

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
6 January 2005 (06.01.2005)

PCT

(10) International Publication Number
WO 2005/000273 A1

(51) International Patent Classification⁷: **A61K 9/14**
(21) International Application Number:
PCT/IT2003/000401

(22) International Filing Date: 27 June 2003 (27.06.2003)

(25) Filing Language: Italian

(26) Publication Language: English

(71) Applicant (for all designated States except US): **BIO-PROGRESS S.P.A.** [IT/IT]; Via Aurelia 58, I-00165 Roma (IT).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **OLIVIERI, Aldo** [IT/IT]; Via Aurelia 58, I-00165 Roma (IT). **BO-NANOMI, Michele** [IT/IT]; Via Brescia 29, I-00198 Roma (IT). **PAZZI, Piergiorgio** [IT/IT]; Via A. De Gasperi 3, I-66050 San Salvo (IT).

(74) Agent: **TANSINI, Elio, Fabrizio**; Bugnion S.p.A., Viale Lancetti, 17, I-20158 Milano (IT).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: COMPOSITE PRODUCT OBTAINABLE BY COGRINDING OF A ACTIVE PRINCIPLE WITH A COPOLYMER N-VINYL-2-PYRROLIDONE/VINYL-ACETATE

Carrier	Example	Nimesulide / Carrier Ratio	Activation time (hours)					
			0		1		2	
			ΔH_f (mJ/mg)	T_f (°C)	ΔH_f (mJ/mg)	T_f (°C)	ΔH_f (mJ/mg)	T_f (°C)
NVP/VA	3	1 / 3	60.6	137.3	34.7	114.9	26.0	108.5
	4	1 / 4	59.6	140.2	19.0	109.4	10.6	107.7
PVP	E	1 / 3	95.8	149.8	28.5	136.0	21.0	135.4
	F	1 / 4	75.9	149.4	15.0	133.0	15.1	130.5
PVP-CL	G	1 / 3	79.2	150.7	32.9	132.6	31.2	132.0
	H	1 / 4	77.2	150.5	24.6	130.6	23.7	129.6

(57) Abstract: The present invention describes how to obtain composite products comprising an active substance supported by a carrier, in which the carrier is the linear copolymer of N-vinyl-2-pyrrolidone with vinyl acetate. The composite products are obtained by co-grinding of the dry mixture of the active substance and of the aforesaid carrier. The composite products thus obtained have better chemical-physical properties (lower melting enthalpy and/or lower melting temperature of the active substance) and a higher dissolution speed with respect to composite products obtained with the same co-grinding time with other carriers used in prior techniques. Furthermore, the composite products obtained with the technique according to the present invention have the appearance of powders that are easier to work from a pharmaceutical point of view (flow, compression) with respect to composite products previously obtained with other carriers.